



LOCTITE® V1315

July 2007

Description:

V1315 may be used for bonding components which need to withstand high stresses caused by differential thermal expansion, impact or peeling loads, especially when securing engineering materials such as composites and reinforced plastics. Although it cures rapidly at ambient temperatures, the slow initiation allows assembly of components without requiring long jiggling times. The high strength is complimented by the excellent durability.

Physical Properties:	Part A	Part B	Mixed
Colour	Off White	Off White	Off White
Viscosity (mPa.s)			Thixotropic
Specific Gravity	1	1	1
Mix Ratio- By Volume			1.1

Performance:

Shear Strength - Steel (MPa)	15
- Aluminium	20
- GRP	6*
Gap Fill (mm)	~2
Peel Strength (N/25mm)	140

Cure Speed:

Handling Strength	~15 mins.
Working Strength	30-35 mins.
Full Strength	8 hrs.

* denotes substrate failure

Service Temperature:

The recommended service temperature range for this product is -60 to +120°C. However higher temperatures may be endured for short periods providing the adhesive is not unduly stressed.

Storage:

When stored in the original unopened containers at 5-7°C, the shelf life of this product is 12 months from the date of manufacture.

Handling:

Full information can be obtained from the Material Safety Data Sheet (MSDS). Users are reminded that all materials, whether innocuous or not, should be handled according to the principles of good industrial hygiene.

Directions for Use:

1. Though this adhesive will bond through a degree of oil contamination ideally the surfaces should be clean, dry and grease free prior to bonding. Where optimum performance is required then light abrasion (i.e. Emery Cloth or Shot Blasting) is recommended. Surfaces can be degreased using **Loctite 7063**.
2. The adhesive should be dispensed through a static mixer directly onto the components
3. Assemble the parts and squeeze together with sufficient pressure to ensure the adhesive spreads to cover the entire bond area. Apply light clamping pressure and do not disturb, or realign the joint, whilst the adhesive cures.

The information given and the recommendations made herein are based on our experience and are believed to be accurate. No guarantee as to, or responsibility for, their accuracy can be given or accepted, however, and no statement herein is to be treated as a representation or warranty. In every case we urge and recommend that purchasers, before using any product, make their own tests to determine, to their own satisfaction, its suitability for their particular purposes under their own operating conditions.

Henkel Loctite Americas
+860.571.5100

Henkel Loctite Europe
+49.89.9268.0

Henkel Loctite Asia Pacific
+81.45.758.1810

For the most direct access to local sales and technical support visit: www.loctite.com