

## LOCTITE® EA 3472

 Known as LOCTITE® 3472  
 September 2024

### PRODUCT DESCRIPTION

LOCTITE® EA 3472 provides the following product characteristics:

<b>Technology</b>	Epoxy
Chemical type	Epoxy
Appearance (resin)	Grey liquid
Appearance (hardener)	Grey liquid
Appearance (mixed)	Grey
Components	Two components - resin & hardener
Mix Ratio, (by weight) resin : hardener	1 : 1
Mix Ratio, (by volume) resin : hardener	1 : 1
<b>Cure</b>	Room temperature cure after mixing
<b>Application</b>	Industrial maintenance
Application temperature	15°C to 30°C (59°F to 86°F)
Specific benefits	<ul style="list-style-type: none"> <li>• Castable liquid - repairs hard to reach areas</li> <li>• Rebuilds worn parts fast – limits downtime</li> <li>• High steel content - cures to a metal-like finish</li> <li>• Superior adhesion - bonds well to all metal substrates</li> </ul>

LOCTITE® EA 3472 is a two-part steel filled epoxy adhesive that is ideal for the repair and recovery of worn and damaged machinery. Typical applications include repairing worn parts such as shafts, housings, keyways, and flanges, as well as broken or damaged parts including castings, pipes, or fabrications. This product can be used in a variety of jobs including filling cavities, leveling machinery, repairing cast-steel plates, making core molds, applying a sacrificial coating, or sealing leaking pipes. This product is typically used in applications with an operating range of -20 °C to 120 °C (-4°F to 248°F).

### Typical properties of uncured material

#### Resin

Weight per volume	kg/L	2.35
	(lbs/gal)	(19.6)
Viscosity, brookfield – RVF @ 25°C, mPa.s (cP):		100 000
Spindle 7, speed 100 rpm		

#### Hardener

Weight per volume	kg/L	2.35
	(lbs/gal)	(20.45)
Viscosity, brookfield – RVF @ 25°C, mPa.s (cP):		112 500
Spindle 7, speed 20 rpm		

### Typical curing performance

Curing @ 23°C

Pot life (200 g mass), ISO 9514, minutes	40
Working life, minutes	
10°C	180
20°C	60
30°C	40

### Typical performance of cured material

Cured for 1 week @ 23 °C

#### Physical properties:

Tensile Strength, ISO 527-2	N/mm <sup>2</sup> (psi)	6000 (840 000)
Tensile Modulus, ISO 527-2	N/mm <sup>2</sup> (psi)	65 (9 400)
Compressive strength, ISO 604	N/mm <sup>2</sup> (psi)	70 (10 000)
Compressive modulus, ISO 604	N/mm <sup>2</sup> (psi)	6000 (870 000)

#### Adhesive properties

Lap Shear Strength, ISO 4587

Mild steel (grit blasted)	N/mm <sup>2</sup> (psi)	25 (3600)
Aluminum	N/mm <sup>2</sup> (psi)	20 (2900)

**GENERAL INFORMATION**

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Material Safety Data Sheet.

**Directions for use****Surface preparation**

Proper surface preparation is critical to the long-term performance of this product. The exact requirements vary with the severity of the application, expected service life, and initial substrate conditions.

1. Remove dirt, oil, grease, etc. with a suitable cleaner, e.g. high-pressure water cleaning system using LOCTITE® cleaner/degreaser.
2. All skip welds, weld spatter, buckshot, and other surface roughness must be ground down; undercuts and pinholes must be ground and filled. All projections, edges, high points, and fillets must be ground to radius of at least 3mm and all corners must be likewise rounded to maximize product performance.
3. Blast all surfaces to be coated with a sharp edged angular grit to a depth of profile of 75 to 100 microns, and a degree of cleanliness of near white metal (SIS SA 2½ /SSPC-SP 10). For immersion service, a degree of cleanliness of white metal (SIS SA 3/SSPC-SP 5) is required.
4. After blasting, metal surfaces should be cleaned, e.g. with LOCTITE® solvent based, residue free cleaner, and be coated before any oxidation or contamination takes place.
5. Metal that has been in contact with salt solutions, e.g. seawater, should be grit blasted and high-pressure water blasted, left for 24 hours to allow any salts in the metal to sweat to the surface. A test for chloride contamination should be performed. The procedure should be repeated until chloride concentration on the surface is below 30mg/m<sup>2</sup> (3µg/cm<sup>2</sup>). Then blast and clean the surface as described on point 3 and 4 above.

**Application**

1. Mix resin and hardener according to mix ratios listed or transfer entire kit onto a clean and dry mixing surface and mix material vigorously until a uniform color is obtained.
2. Apply material to prepared surface by first forcing a thin layer deep into the texture of the substrate.
3. Then immediately build up to the desired finished thickness.

**Inspection**

1. Visually inspect for pinholes and voids just after application.
2. Once the coating has cured, repeat visual inspection to confirm it is free from pinholes, misses and mechanical damages.
3. Control thickness of the coating, especially in the critical points.

**Coverage**

To achieve a 5 millimeter (0.2 in) thickness, the coverage rate will be 416 cm<sup>2</sup> (64 in<sup>2</sup>) for 0.5 kg (1.1 lb), excluding overthickness, repairs, etc.

**Repairs**

Any voids, pinholes, low thickness areas found in the coating should be repaired by lightly abrading, cleaning and applying further product.

**Clean-up**

Immediately after use, clean tools with LOCTITE® solvent based cleaner. Once cured, the material can only be removed mechanically.

**Storage**

Store product in the unopened container in a dry location. Storage information may be indicated on the product package labeling.

**Optimal Storage: 8°C to 21°C. Storage below 8°C or greater than 28°C can adversely affect product properties.**

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel representative.

**Product specification**

The technical data contained herein are intended as reference only and are not considered specifications for the product. Product specifications are located on the Certificate of Analysis or please contact Henkel representative.

**Approval and Certificate**

Please contact Henkel representative for related approval or certificate of this product.



**Data ranges**

The data contained herein may be reported as a typical value. Values are based on actual test data and are verified on a periodic basis.

Temperature/Humidity Ranges: 23°C / 50% RH = 23±2°C / 50±5% RH

**Conversions**

(°C x 1.8) + 32 = °F

kV/mm x 25.4 = V/mil

mm / 25.4 = inches

µm / 25.4 = mil

N x 0.225 = lb

N/mm x 5.71 = lb/in

N/mm<sup>2</sup> x 145 = psi

MPa x 145 = psi

N·m x 8.851 = lb·in

N·m x 0.738 = lb·ft

N·mm x 0.142 = oz·in

mPa·s = cP

**Disclaimer**

The information provided in this Technical data sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical data sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 2