

LOCTITE® EA 9492LI

February 2021

PRODUCT DESCRIPTION

LOCTITE® EA 9492LI provides the following product characteristics:

| | |
|---|--|
| Technology | Epoxy |
| Chemical type (resin) | Epoxy |
| Chemical type (hardener) | Modified amine |
| Appearance (resin) | White opaque paste |
| Appearance (hardener) | Grey, opaque liquid |
| Appearance (mixed) | White opaque paste |
| Components | Two part - Resin & Hardener |
| Mix Ratio, (by weight) resin : hardener | 2 : 1 |
| Mix Ratio, (by volume) resin : hardener | 100 : 50 |
| Cure | Room temperature cure after mixing |
| Application | Bonding & potting |
| Specific benefits | <ul style="list-style-type: none"> • Very low outgassing • High temperature resistance • Excellent solvent resistance |

LOCTITE® EA 9492LI is a high temperature resistant, two component epoxy adhesive. It is a lower viscosity version of LOCTITE EA 9492 and retains the high performance features of this product. It is a general purpose adhesive that bonds and repairs a wide variety of materials. Fully cured LOCTITE® EA 9492LI bonds offer superior thermal shock resistance, mechanical, electrical and impact resistant properties.

Typical properties of uncured material

Resin

| | |
|---|-------------------|
| Specific gravity @ 25°C | 1.52 to 1.56 |
| Viscosity, Brookfield - RVT, 25°C, mPa·s (cP): Spindle 6, speed 5 rpm, | 50,000 to 120,000 |
| Viscosity, DIN 54453, mPa·s (cP): Shear rate 10s ⁻¹ | 45,000 |
| Shear rate 100s ⁻¹ | 34,000 |
| Flash point - see SDS | |

Hardener

| | |
|---|------------------|
| Specific gravity @ 25°C | 1.5 to 1.58 |
| Viscosity cone plate 4 cm, STM 738, @ 25°C and 40 s ⁻¹ , mPa·s (cP) | 20,000 to 45,000 |
| Flash point - see SDS | |

Typical curing performance

Mixed properties

| | |
|---------------------------------------|----------|
| Pot life @ 22°C, minutes 100g mass | 10 to 30 |
| Pot life @ 22°C, minutes 100g mass | 6 |

Fixture time

Fixture time is defined as the time to develop a shear strength of 0.1 N/mm².

| | |
|---|----|
| Fixture time, mixed, @ 22°C, minutes | 75 |
| Thin film set (500microns film, RT, on glass strips), minutes | 90 |
| Shore D hardness, 7d RT, shore D unit | 85 |
| DSC Tg, 2nd scan, °C | 95 |

Typical performance of cured material Adhesive Properties

| | |
|--|-----|
| Cured for 1 day @ RT + 1 day @ 65°C Aluminum (grit blasted) | >13 |
|--|-----|

General information

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

Residues of mixed product, before complete cure has occurred, can be washed out from surfaces, clothes, hands by simply washing with warm soapy water.

Material Safety Data Sheet (MSDS) for EA 9492 Part A and EA 9492LI Part B are available.

For safe handling information on this product, consult the Safety Data Sheet (SDS).

Where aqueous washing systems are used to clean the surfaces before bonding, it is important to check for compatibility of the washing solution with the adhesive.

Directions for use

1. For best performance surfaces for bonding should be clean, dry and free of grease. For high strength structural bonds, special surface treatments can increase the bond strength and durability.
2. To use, resin and hardener must be blended. Product can be applied directly from dual cartridges by dispensing through the mixer head supplied. Discard the first 3 to 5 cm of bead dispensed. Using bulk containers, mix thoroughly by weight or volume in the proportions specified in the Product Description Matrix. For hand mixing, weigh or measure out the desired amount of resin and hardener and mix thoroughly. Mix approximately 15 seconds after uniform color is obtained.
3. It is recommended that this product is not mixed and cured in bulk quantities of greater than 0.5 kg as excessive heat build-up can occur. Mixing smaller quantities will minimize the heat build-up.
4. Apply the adhesive as quickly as possible after mixing to one surface to be joined. For maximum bond strength apply adhesive evenly to both surfaces. Parts should be assembled immediately after mixed adhesive has been applied.
5. For working life please see section 'Typical Properties of Uncured Material'. Higher temperatures and larger quantities will shorten this working time.
6. Excess uncured adhesive can be wiped away with organic solvent (e.g. acetone).
7. Keep the assembled parts from moving during cure. The joint should be allowed to develop full strength before subjecting to any service loads.
8. After use and before adhesive hardens, mixing and application equipment should be cleaned with hot soapy water.

Please, refer to a Henkel Engineer for further information.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product package labeling.

Optimal Storage: 8°C to 28°C. Storage below 8°C or greater than 28°C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel representative.

Product specification

The technical data contained herein are intended as reference only and are not considered specifications for the product. Product specifications are located on the Certificate of Analysis or please contact Henkel representative.

Data ranges

The data contained herein may be reported as a typical value. Values are based on actual test data and are verified on a periodic basis.

Temperature/Humidity Ranges: 23°C / 50% RH = 23±2°C / 50±5% RH

Approval and Certificate

Please contact Henkel representative for related approval or certificate of this product.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$

$\text{kV/mm} \times 25.4 = \text{V/mil}$

$\text{mm} / 25.4 = \text{inches}$

$\mu\text{m} / 25.4 = \text{mil}$

$\text{N} \times 0.225 = \text{lb}$

$\text{N/mm} \times 5.71 = \text{lb/in}$

$\text{N/mm}^2 \times 145 = \text{psi}$

$\text{MPa} \times 145 = \text{psi}$

$\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$

$\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$

$\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$

$\text{mPa}\cdot\text{s} = \text{cP}$



Disclaimer

The information provided in this Technical data sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical data sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1